

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A method of manufacturing a microelectronic device, comprising:
 - forming a patterned feature ~~over~~ on a substrate;
 - depositing a conformal polymer layer ~~over~~ on the patterned feature and the substrate, wherein such depositing employs a fluorine-containing plasma source;
 - etching the polymer layer to expose the patterned feature and a portion of the substrate, thereby forming polymer spacers on opposing sides of the patterned feature; and
 - forming an insulating layer ~~over~~ on the polymer spacers.
2. (Original) The method of claim 1 wherein the conformal polymer layer is deposited in a chemical reactive plasma environment.
3. (Original) The method of claim 1 wherein the substrate comprises diamond.
4. (Original) The method of claim 1 wherein the substrate comprises strained silicon.
5. (Original) The method of claim 1 wherein the patterned feature is a semiconductor device gate structure.
6. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises CF₄.

7. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises CF_3 .

8. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises C_2F_2 .

9. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises CH_2F_2 .

10. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises CHF_3 .

11. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises C_2F_6 .

12. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises C_3F_8 .

13. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises SF_6 .

14. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises C_3F .

15. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises CH_3F .

16. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source comprises a fluorocarbon.

17. (Previously Presented) The method of claim 1 wherein a flow rate of the fluorine-containing plasma source ranges between about 5 sccm and about 200 sccm.

18. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source further includes a chlorine-containing gas.

19. (Original) The method of claim 18 wherein the chlorine-containing gas comprises Cl_2 and chlorocarbons.

20. (Previously Presented) The method of claim 1 wherein the fluorine-containing plasma source further includes a bromine-containing gas.

21. (Original) The method of claim 20 wherein the bromine-containing gas comprises HBr.

22. (Original) The method of claim 1 wherein the etching employs an oxygen-containing gas.

23. (Original) The method of claim 22 wherein the oxygen-containing gas comprises O_2 .

24. (Original) The method of claim 22 wherein the oxygen-containing gas comprises O_3 .

25. (Original) The method of claim 22 wherein the oxygen-containing gas comprises NO_2 .

26. (Original) The method of claim 22 wherein the oxygen-containing gas comprises CO₂.

27. (Original) The method of claim 22 wherein the oxygen-containing gas comprises CO.

28. (Previously Presented) The method of claim 1 wherein the step of depositing the polymer layer employs a direct current (DC) bias applied to the substrate ranging between about 1 Watts and about 50 Watts.

29. (Previously Presented) The method of claim 1 wherein the step of depositing the polymer layer employs a radio frequency (RF) bias applied to the substrate ranging between about 1 Watts and about 50 Watts.

30. (Original) The method of claim 1 wherein the etching the spacer employs a direct current (DC) bias applied to the substrate ranging between about 1 Watts and about 500 Watts.

31. (Original) The method of claim 1 wherein the etching the spacer employs a radio frequency (RF) bias applied to the substrate ranging between about 1 Watts and about 500 Watts.

32. (Previously Presented) The method of claim 1 further comprising:
forming source/drain regions in the substrate on opposing sides of the patterned feature.

33. (Original) The method of claim 32 wherein removing the spacers includes etching the spacers with an oxygen-containing gas.

Claims 34-36 (Cancelled).

37. (Previously Presented) A method of manufacturing a microelectronic device, comprising:

- forming a doped well in a substrate;
- forming a gate stack over the doped well;
- forming, in-situ, polymer spacers on opposing sides of the gate stack by:
 - employing a substrate bias and a fluorine-containing plasma source to deposit a conformal polymer layer over the gate stack; and
 - adjusting the substrate bias, without removing the substrate bias, to etch the polymer layer with the fluorine-containing plasma, thereby exposing the gate stack and defining the polymer spacers; and
 - forming an insulating layer over the polymer spacers.

38. (Previously Presented) The method of claim 37 wherein forming the doped well includes:

- employing a high density plasma source to form the doped well, the high density plasma source having a carbon-to-deuterium ratio ranging between about 0.1 percent and about 5 percent in a process ambient, wherein the process ambient pressure ranges between about 0.1 mTorr and about 500 Torr and the substrate is held at a temperature ranging between about 150°C and about 1100°C; and
- treating the doped well by employing a deuterium-containing plasma.

39. (Previously Presented) The method of claim 37 further comprising:

forming source/drain regions in the doped well via ion implantation before the step of forming the insulating layer, wherein forming the source/drain regions includes employing the polymer spacers to laterally limit formation of the source/drain regions during the ion implantation; and

forming contact regions over the source/drain regions and contacting the polymer spacers, before the step of forming the insulating layer.